

	Acoustic Neo		
Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	3,2
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2 , 4
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m2	2,5
CLASSIFICATION			
Product specification	EN 651		✓
European classification	EN 685	class	34/42
Residual indentation	EN ISO 24343	max. mm	0,2
Dimensional stability	EN ISO 23999	max. %	0,2
Light fastness	EN ISO 105-B02	grade	6
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	Bfl-s1
Impact sound reduction	EN ISO 140-8	DL _w (dB)	17
Slip resistance	DIN 51130		R9
Electrical resistance	EN 1815	kV	< 2
	EN 1081	Ω	≤ 10 ¹⁰
Chemical resistance	ASTM F 925		✓
Bacterial resistance	EN ISO846:1999		✓
Castor chair resistance	EN 425		✓
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Seaming method			heat or cold weld
Warranty		year	7
CE MARKING	EN 14041		✓

GRABOPLAST Floor Covering Manufacturers Ltd.
 H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
 mail@graboplast.hu www.graboplast.hu